

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

LISTING OF CLAIMS:

1. (withdrawn) A method for preserving the ratio of the tensile strength in the length direction to the tensile strength in the breadth direction of a mat of filaments which is in displacement, passing from one conveyor to another, characterized in that the mat is subjected to a vacuum applying it to a support during the passage from the first conveyor to a movable element.

2. (withdrawn) The method as claimed in claim 1, characterized in that the mat is slowed while it passes from the first conveyor to the movable element.

3. (withdrawn) The method as claimed in claim 1, characterized in that the first conveyor is that onto which the filaments for forming the mat are deposited.

4. (currently amended) An installation for producing a nonwoven fabric, comprising a spun-bonding tower depositing a mat of filaments onto a first conveyor, the

first conveyor being arranged to deliver the mat to
transfer means for causing the mat of filaments to pass
onto a first movable conveying element for supporting the
mat during consolidation, the mat being free of prior
consolidation, and consolidation means for consolidating
the mat supported on the first movable conveying element by
entanglement, the mat being delivered on a first movable
conveying element to means for consolidation by
entanglement, and means intended for causing the mat of
filaments to pass onto the first movable conveying element,
characterized in that the transfer means intended for
causing the mat of filaments to pass onto the first movable
conveying element comprise a second movable conveying
element having a device for the application of a vacuum
which maintains the mat on an outer surface of the second
movable conveying element, the first conveyor and the first
movable conveying element each include an elongate
generally flat run along which the mat is conveyed and
supported, and the first conveyor is more air-permeable
than the first movable conveying element.

5. (previously presented) The installation as claimed
in claim 4, characterized in that the second movable
element is a drum or a conveyor.

6. (currently amended) The installation as claimed in claim 4, characterized in that ~~the first conveyor is more air-permeable than the first movable element~~ the consolidation means include fluid impingement of the mat and the lesser air-permeability of the first movable conveying element more fully supports the mat to enhance filament entanglement by the fluid impingement as compared with the first conveyor, thereby enhancing consolidation and preservation of the ratio of the tensile strength in the length direction to the tensile strength in the breadth direction.

7. (original) The installation as claimed in claim 6, characterized in that the first conveyor has an air permeability of between 500 and 1100 CFM (14.1 and 31 m³/min).

8. (currently amended) The installation as claimed in ~~claim 5~~ claim 7, characterized in that the first movable conveying element has an air permeability of between 50 and 500 CFM (1.41 and 14.1 m³/min).

9. (previously presented) The installation as claimed in claim 4, characterized in that the first conveyor is a multilayer cloth, while the first movable conveying element is a single layer cloth.

10. (currently amended) The installation as claimed in claim 4, characterized in that the first conveyor delivers the mat directly to the transfer means ~~intended for causing the mat of filaments to pass.~~

11. (currently amended) The installation as claimed in claim 4, characterized in that the first movable conveying element has a suction device which cooperates with the transfer means ~~for causing the mat to pass~~, in order to facilitate the passage of the mat from the means to the first movable conveying element.

12. (previously presented) The installation as claimed in claim 4, characterized in that said installation is constructed and arranged to preserve the ratio of the tensile strength in the length direction to the tensile strength in the breadth direction of said mat of filaments which is in displacement, coming from said spun-bonding

tower and going to said means for consolidation by entanglement.

13. (previously presented) The installation as claimed in claim 4, characterized in that said conveyor operates at a conveyor linear speed to convey said mat of filaments and said second movable conveying element operates at a conveying element linear speed to cause said mat of filaments to pass onto said first movable conveying element, and said second conveying element linear speed is less than said conveyor linear speed.

14. (new) An installation for producing a nonwoven fabric comprising a spun-bonding tower depositing a mat of filaments onto a first conveyor, transfer means for causing the mat of filaments to pass from the first conveyor onto a first movable conveying element for supporting the mat during consolidation, the mat being free of prior consolidation, and consolidation means for impinging fluid on the mat and consolidating the mat as it is supported on the first movable conveying element, characterized in that the transfer means for causing the mat of filaments to pass onto the first movable conveying element comprise a second movable conveying element having a device for the

application of a vacuum which maintains the mat on an outer surface of the second movable conveying element, the first conveyor and the first movable conveying element each having an elongate generally flat run along which the mat is conveyed and supported, and the first conveyor is more air-permeable than the first movable conveying element to more fully support the mat during consolidation to improve the filament entanglement by the impinging fluid, and to thereby enhance consolidation and preservation of the ratio of the tensile strength in the length direction to the tensile strength in the breadth direction as compared with the corresponding ratio provided by an identical consolidation of an identical mat on the first conveyor.

15. (new) The installation as claimed in claim 14, wherein the tensile strength in the length direction and tensile strength in the breadth direction are greater than the corresponding tensile strengths provided by an identical consolidation of an identical mat on the first conveyor.

16. (new) The installation as claimed in claim 15, wherein the conveyor operates at a conveyor linear speed to convey the mat of filaments and the second movable

conveying element operates at a conveying element linear speed to cause said mat of filaments to pass onto the first movable conveying element, and the second movable conveying element linear speed is less than the conveyor linear speed.